



Management Procedure 2575
Revision: A
Date Issued: July 21, 2004
Date Revised:

Calibration Procedure

DeFelsko Corporation

PosiTest DFT Ferrous

Coating Thickness Gages

Table of Contents

1	Introduction and UUC Performance Requirements	2
	Table 1-1 Measurement Ranges	2
	Table 1-2 UUC Calibration Requirements and Calibration Description	2
2	Measurement Standards and Support Equipment Performance Requirements.....	2
	Table 2-1 Measurement Standards & Support Equipment Performance Requirements	3
3	Preliminary Operations	3
4	Calibration Process.....	3
	Figure 4-1 Measurement Area	4
5	Performance Requirements	4
	Table 5-1 Performance Requirements and Calibration Data for PosiTest DFT Ferrous	4
	Management Procedure Change Notice	5

1 Introduction and UUC Performance Requirements

1.1 This procedure describes the calibration of Coating Thickness Gages, PosiTest DFT Ferrous. All gages have the following ranges:

Table 1-1 Measurement Ranges

Gage	Measurement Range
DFT Ferrous	0-1000 μm , 0-40 mils

1.2 The unit being calibrated will be referred to as the UUC (unit-under-calibration).

1.3 UUC Environmental Range:

- Temperature: $23 \pm 5^\circ \text{C}$.
- Relative Humidity: Up to 95%

1.4 UUC Warm-up and Stabilization Period requirements: Does not apply.

Table 1-2 UUC Calibration Requirements and Calibration Description

Unit-Under-Test (UUC) Parameter or Function		Performance Specifications	Test Method
1.1	Accuracy Test DFT Ferrous	$\pm (2 \mu\text{m} + 3\% \text{ of reading})$ $\pm (0.1 \text{ mils} + 3\% \text{ of reading})$	Compared to Coating Thickness Reference Standards.

2 Measurement Standards and Support Equipment Performance Requirements

2.1 Minimum-Use-Specifications are the calculated minimum performance specifications required for the measurement standards and support equipment to be utilized for comparison measurements required in the Calibration Process.

2.2 The Minimum-Use-Specifications are developed through uncertainty analysis and are calculated through assignment of a defined and documented uncertainty ratio or margin between the specified tolerances of the UUC and the capabilities (uncertainty specifications) required of the measurement standards system.

2.3 The uncertainty ratios applied in this Calibration Procedure are 4:1 or better.

Caution: The instructions in this Calibration Procedure relate specifically to the equipment and conditions listed in Section 2. If other equipment is substituted, the information and instructions must be interpreted accordingly.

Measurement Standards & Support Equipment
Environmental Requirements:

Temperature: $23 \pm 5^\circ \text{C}$.
Relative Humidity: Less than 95%

Measurement Standards & Support Equipment
Warm-up and Stabilization Requirements:

Not Required

Table 2-1 Measurement Standards & Support Equipment Performance Requirements

Equipment Generic Name (Quantity)	Minimum-Use-Specifications		Manufacturer/Model #'s Applicable
	Range	Accuracy	
2.1 Coating Thickness Reference Standards	0-1000 μm	$\pm 0.25 \mu\text{m}$	DeFelsko Corporation, Thickness Calibration Standards, Model CAL-S2
	0-40 mils	$\pm 0.01 \text{ mils}$	

3 Preliminary Operations

Note: Review the entire document before starting the calibration process.

3.1 Visual Inspection

3.1.1 Visually inspect the UUC for:

- Damaged LCD readout
- probe wear or coating
- cracked or broken case
- missing battery door or other parts
- proper identification

3.1.2 Damage or excess wear should be repaired prior to beginning the calibration process.

4 Calibration Process

Note: Whenever the test requirement is not met, verify the results of each test and take corrective action before proceeding.

4.1 Turn gage on. Perform Reset. Perform Zero check on uncoated reference standard. If zero check is outside of allowable range, perform zero function and recheck uncoated reference standard.

4.2 Accuracy Test


4.2.1 Review the Performance Requirements Table 5-1.

4.2.2 Using the appropriate Certificate of Calibration template for the UUC, record the reference material values on the form.

4.2.3 Determine the allowed range of readings using the calculation methods shown in columns D and E of Table 5-1.

- 4.2.4 Use the UUC to make readings of the applicable reference standard. Verify that the readings are within the allowable limits determined in 4.2.3. Record the reference standard values and the readings on the Certificate of Calibration. *Note:* Record all digits displayed on the LCD.
- 4.2.5 In making readings the probe tip should be centered on the Coating Thickness Reference Standard. If not directly in the center, the reading should be taken at least 0.6 cm from the edge of the standard as shown in Figure 4-1.

Figure 4-1 Measurement Area



5 Performance Requirements

Note: The technician should collect the data needed to complete columns B and C of the appropriate table below. Do not write in this procedure.

Table 5-1 Performance Requirements and Calibration Data for PosiTest DFT Ferrous

Nominal Thickness	Reference Standard	UUC Indication or Reading *		
		Gage Measurement	Min. Reading Allowed	Max. Reading Allowed
A	B	C	D	E
0 microns	uncoated	0 microns	- 2 microns	+ 2 microns
76 microns			0.97 x B - 2 microns	1.03 x B + 2 microns
254 microns				
508 microns				

* For metric readings convert using 1 mil = 25.4 microns

